

## Player's Choice

### CLASSIFICATION:

- Modified acrylic floor finish

### PACKAGING:

Jug	Pail	Drum
4L	18.9L	210L

### DESCRIPTION:

- **Player's Choice** Floor Finish is a high solids product, providing application labour savings by requiring fewer coats in comparison to conventional finishes.
- **Player's Choice** is a low odour product in comparison to other high solids finishes and provides an appealing 'wet look' finish to treated floors.
- **Player's Choice** Floor Finish has optimum maintenance flexibility, allowing for use in burnishing, low speed spray buffing, or low maintenance systems.
- **Player's Choice** Floor Finish is completely white in both liquid and dried forms, undergoing no yellowing / discolouration caused by age or uv light.

### CHEMICAL AND PHYSICAL PROPERTIES:

- |                         |                     |
|-------------------------|---------------------|
| • Appearance            | White opaque liquid |
| • Odour                 | Mild acrylic        |
| • pH                    | 7.5 – 8.5           |
| • Specific Gravity      | 1.03                |
| • Viscosity             | Less than 25 cps    |
| • Nonvolatiles / Solids | 25%                 |

### USE DIRECTIONS:

- **Application:** Prepare floor by scrubbing with a Sanilabs neutral cleaner or Sanilabs Tuff-Scrub, or by stripping with a Sanilabs stripper according to label directions. Rinse well. Apply **Player's Choice** Floor Finish undiluted in uniform coats (35-75 m<sup>2</sup>/L; 1500-3000 ft<sup>2</sup>/ US gal) with a clean floor finish string mop or flat mop. Allow adequate dry time between coats (30 minutes minimum, or 15 minutes after dry to touch, whichever is longer). No sealer is typically required, except for very porous floors (e.g. terrazzo), or if additional stain resistance is needed.
- **Maintenance:** Dust mop and clean daily using a Sanilabs neutral cleaner or maintainer. **Player's Choice** Floor Finish may be maintained as required by burnishing (1000-3000 rpm) using a synthetic burnishing pad, by low speed (175-350 rpm) spray buffing using a red pad, or by cleaning alone.

*See Material Safety Data Sheet for proper handling and safety instructions.*